

DELO[®] KATIOBOND[®] 4670

modified epoxy resin | 1C | UV-curing

free of solvents | humidity-resistant, electrically insulating, self-leveling, tension-equalizing, flowable, filled, high ion purity

Special features of product

- compliant with RoHS Directive 2015/863/EU
- halogen-free according to IEC 61249-2-21
- compliant with limits of VOC content in adhesive acc. to GB33372-2020
- passes ANSI/UL 94 HB Flame Test

Function

- Fill for Dam&Fill
- glob top
- encapsulant / potting compound

Typical area of use

- smart card applications
- encapsulation of chip modules

Curing

Suitable lamp types LED 365 nm, UVA

Typical irradiation time

intensity 55 - 60 mW/cm² 60 s
UVA

intensity 150 mW/cm² 30 s
LED 365 nm

at +70 °C

Processing

Typical adhesive application needle dispensing

Conditioning time (typical)

in containers up to 1,000 ml 6 h

in containers up to 10 l 15 h

Processing time

tumble before processing for 3 h 1 – 2 1/min conditioned containers in containers up to 1,000 ml	24	h
tumble before processing for 6 h 1 – 2 1/min conditioned containers in containers up to 10 l	24	h

Storage life in unopened original container

at 0 °C to +10 °C	6	month(s)
-------------------	---	----------

Technical properties

Color in cured condition in 0.1 mm layer thickness	gray
Transparency in cured condition in 0.1 mm layer thickness	transparent
Filler particle type	minerals
Filler particle size	d98 = 32 µm

Parameters

Density <i>DELO Standard 13 liquid</i>	1.4	g/cm ³
Viscosity <i>liquid Viscosimeter</i>	4800	mPa·s
Compression shear strength <i>DELO Standard 5 Glass AI 60 mW/cm² 60 s Plus at approx. +23 °C 24 h</i>	10	MPa
Compression shear strength <i>DELO Standard 5 Glass Glass 60 mW/cm² 60 s Plus at approx. +23 °C 24 h</i>	20	MPa
Tensile strength <i>by the criteria of DIN EN ISO 527 60 mW/cm² 120 s Plus at approx. +23 °C 24 h</i>	30	MPa
Elongation at tear <i>by the criteria of DIN EN ISO 527 60 mW/cm² 120 s Plus at approx. +23 °C 24 h</i>	6	%
Young's modulus <i>by the criteria of DIN EN ISO 527 60 mW/cm² 120 s Plus at approx. +23 °C 24 h</i>	1700	MPa
Shore hardness D <i>by the criteria of DIN EN ISO 868 60 mW/cm² 120 s Plus at approx. +23 °C 24 h</i>	79	

Glass transition temperature <i>DMTA 365 nm 150 mW/cm² 30 s Plus at approx. +23 °C 24 h</i>	55	°C
Coefficient of linear expansion <i>DELO Standard 26 TMA Evaluation T: 30 °C - 150 °C 60 mW/cm² 60 s Plus at approx. +23 °C 24 h</i>	150	ppm/K
Shrinkage <i>DELO Standard 13 60 mW/cm² 60 s Plus at approx. +23 °C 24 h</i>	3	vol. %
Water absorption <i>by the criteria of DIN EN ISO 62 Layer thickness: 2 mm 365 nm 150 mW/cm² 30 s Plus at approx. +23 °C 24 h Type of storage: Media Medium: Distilled water Duration: 24 h</i>	0.19	%
Decomposition temperature <i>DELO Standard 36 60 mW/cm² 60 s</i>	280	°C
Extractable ions <i>Ion: Chloride</i>	≤10	ppm
Extractable ions <i>Ion: Fluoride</i>	≤100	ppm
Extractable ions <i>Ion: Potassium</i>	≤10	ppm
Extractable ions <i>Ion: Sodium</i>	≤10	ppm
Relative permittivity <i>by the criteria of RF-IV 1 MHz</i>	3.3	
Relative permittivity <i>by the criteria of RF-IV 1 GHz</i>	3.0	
Relative permittivity <i>by the criteria of RF-IV 10 MHz</i>	3.3	
Relative permittivity <i>by the criteria of RF-IV 100 MHz</i>	3.2	

Converting table

°F = (°C x 1.8) + 32	1 MPa = 145.04 psi
1 inch = 25.4 mm	1 GPa = 145.04 ksi
1 mil = 25.4 µm	1 cP = 1 mPa·s
1 oz = 28.3495 g	1 N = 0.225 lb

General curing and processing information

The adhesive can be tumbled during conditioning if necessary, depending on the chemical basis and container size. After tumbling, a waiting time of 1 – 2 h must be maintained to enable air bubbles to escape.

Alternatively, a pressure tank with integrated stirring element can be used to keep the material continuously homogeneous.

The viscosity may decrease during tumbling. Cartridges are excluded from tumbling.

Further information can be found in the instructions for use. The curing time stated in the technical data was determined in the laboratory. It can vary depending on the adhesive quantity and component geometry and is therefore a reference value. Increasing or decreasing the curing temperature and / or irradiation intensity and / or irradiation time shortens or prolongs the curing time and can lead to changed physical properties. All curing or light fixation parameters depend on material thickness and absorption, adhesive layer thickness, lamp type and distance between lamp and adhesive layer. Curing until final strength proceeds within 24 hours at room temperature. High temperatures during or after curing can lead to post-crosslinking of the adhesive which influences the physical properties of the bond. Values measured after 24 h at approx. 23 °C / 50 % r.h., unless otherwise specified.

General

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose.

Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent.

All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

Instructions for use

You can find further details in the instructions for use.

The instructions for use are available on www.DELO-adhesives.com.

We will be pleased to send them to you on demand.

Occupational health and safety

See material safety data sheet.

Specification

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. This Technical Datasheet is for reference only and does not constitute a product specification. Please ask our responsible Sales Engineer for the applicable product specification which includes defined ranges. DELO is neither liable for any values and content of this Technical Datasheet nor for oral or written recommendations regarding the use, unless otherwise agreed in writing. This limitation of liability is not applicable for damages resulting from intent, gross negligence or culpable breach of cardinal obligations, nor shall it apply in case of death or personal injury or in case of liability under any applicable compulsory law.

CONTACT

DELO Industrial Adhesives
Headquarters

▶ Germany · Windach / Munich ... www.DELO-adhesives.com

ADHESIVES

DISPENSING

CURING

CONSULTING